



Test Report

No. SH6084295/TX

Date: Sep 5, 2006

Page 1 of 3

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : One sample of PVC

Test Performed : Selected test(s) as requested by applicant


Sample Receiving Date : AUG, 29, 2006

Test Performing Date : SEP, 01, 2006

Test Result(s) : For further details, please refer to the following page(s).

Signed for and on behalf of
SGS-CSTC Ltd.

Candy Ju (Account Executive)



SGS

TEST REPORT

No. : SC070620222

Date : July 4, 2007

Page: 2 of 2

Test result:

No.	Test item	Standard require	Test result	Conclusion
①	Minimum residual length,(mm)	>0	397	Pass
②	Average residual length,(mm)	≥150	426	Pass
③	Average effluent temperature,(°C)	≤200	144	Pass
④	Flame height	<150, No molten dropper ignite the filter paper.	meet the require	Pass

Test Item	Test Required	Conclusion
DIN 4102-1-1998	Class B1	Pass

- The test was carried out by external laboratory assessed as competent.

*****End of report*****

This Test Report is issued by the Company subject to its General Conditions of Service printed overleaf or attached. Said Conditions are also available upon request or are accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional policies set forth therein. The results shown in this Test Report refer only to the sample(s) tested unless otherwise stated and such sample(s) are retained for 90 days. This Test Report shall not be reproduced except in full, without written approval of the Company.

SGS S.p.A. - Via ...
 SGS (Shanghai) Co., Ltd.
 中国·上海·浦东新区世纪大道1500号17楼

1 (85-21) 2018223 7 (85-21) 25183122
 1 (86-21) 68117128 7 (86-21) 68117128

SHTIL 034046

www.sgs.com